

ALL TESTING CONDUCTED BY:

**FINAL REPORT**  
THIS REPORT AND DATA WITHIN  
HAS COMPLETED QA/QC  
REVIEW.



**CLARK**  
TESTING

Fuels & Lubrication Lab  
1801 Route 51 South  
Building 9  
Jefferson Hills, PA 15025  
Ph: 412-387-1001  
Fax: 412-387-1028

## DURAVI GEAR OIL ADDITIVE

### TIMKEN EP

ASTM D2782

#### TEST SET 1A

**BASELINE MEDIA:** Shell Syn Spirax Gear Oil (80w140)

**DATE CONDUCTED:** 23 AUG 2010

D2782 Timken EP	8/23/2010
Pass (lbs)	75.00
Fail (lbs)	80.00

#### TEST SET 1B

**BASELINE MEDIA:** Shell SSGO w/t Duravi Gear Oil Additive

**DATE CONDUCTED:** 23 AUG 2010

D2782 Timken EP	8/23/2010
Pass (lbs)	100.00
Fail (lbs)	+ 100.00

#### ADDITIONAL NOTES FROM LAB:

- Duravi GOA increased the Smooth Scar Pass Rating of the Base Media by approx. 33%
- Duravi GOA increased the Scoring Fail Rating of the Base Media by > 25%
- Duravi GOA surpassed the test parameters for Scoring Fail Rating @ > 100 lbs