

ALL TESTING CONDUCTED BY:

FINAL REPORT
THIS REPORT AND DATA WITHIN
HAS COMPLETED QA/QC
REVIEW.



CLARK
TESTING

Fuels & Lubrication Lab
1801 Route 51 South
Building 9
Jefferson Hills, PA 15025
Ph: 412-387-1001
Fax: 412-387-1028

DURAVI PENETRATING & LUBRICATING SPRAY

FALEX EP LUBE – PIN & VEE

ASTM D1831

BASELINE MEDIA: Duravi psl

DATE CONDUCTED: 26 MAR 2024

| Falex EP Lube (Pin and Vee) | | Test Code: D3233A method: D3233 A |
|---|------------|-----------------------------------|
| Result Date | 03/26/2024 | |
| Test 1 Direct Load | +2885 lbs | |
| Test 1 Reference Load | +4500 lbs | |
| Test 2 Direct Load | +2885 lbs | |
| Test 2 Reference Load | +4500 lbs | |
| Average Direct Load | +2885 lbs | |
| Average Reference Load | +4500 lbs | |
| Comments | | |
| Temperature at end of first test = 190°F. Temperature at end of second test = 160°F. | | |