

**ALL TESTING CONDUCTED BY:**

**FINAL REPORT**  
THIS REPORT AND DATA WITHIN HAS  
COMPLETED QA/QC REVIEW.



**CLARK**  
TESTING

Fuels & Lubrication Lab  
1801 Route 51 South  
Building 9  
Jefferson Hills, PA 15025  
Ph: 412-387-1001  
Fax: 412-387-1028

## **DURAVI HYDRAULIC OIL ADDITIVE**

### **FZG GEAR TEST - ISO**

ISO 14635-1

**BASELINE MEDIA:** WCH AW 46 w/t Duravi Gear Oil Additive

**DATE CONDUCTED:** 16 FEB 2017

| <b>FZG Gear Test - ISO</b> |    | Test Code: ISO 14635-1 - 14 Stage FZG / Method: ISO 14635-1 |
|----------------------------|----|---|
| Result Date                |    | 02/16/2017  |
| Pass Load Stage            |    | 14  |
| Total Wt. Loss             | mg | 282.5   |

- The test consists of 14 load stages.
- After every stage, the torque of the pinion is increased.
- The defined running time per load stage is 15 min.

**\*\*\*Media Base w/t Duravi Gear Oil Additive surpassed test parameters @ > Stage 14\*\*\***