## **ALL TESTING CONDUCTED BY:**

## **FINAL REPORT**

THIS REPORT AND DATA WITHIN HAS COMPLETED QA/QC REVIEW.



## **DURAVI GP GREASE ROLL STABILITY**

**ASTM D1831** 

**BASELINE MEDIA:** Duravi GP Grease DATE CONDUCTED: 01 APR 2024

Roll Stability	Test Code: D1831 method: D1831
Result Date	04/01/2024
1/4 PENETRATION BEFORE	114
1/4 PENETRATION AFTER	109
Full Cup Conversion - Penetration Before	452
Full Cup Conversion - Penetration After	433
Change	-4.20 %
Temperature	75.0 °C
Time	2 Hours