

ALL TESTING CONDUCTED BY:

FINAL REPORT
THIS REPORT AND DATA WITHIN
HAS COMPLETED QA/QC
REVIEW.



CLARK
TESTING

Fuels & Lubrication Lab
1801 Route 51 South
Building 9
Jefferson Hills, PA 15025
Ph: 412-387-1001
Fax: 412-387-1028

DURAVI GEAR OIL ADDITIVE

FOUR BALL EP LUBE TEST - OIL

ASTM D2783

TEST SET 1A

BASELINE MEDIA: Shell Syn Spirax Gear Oil (80w140)

DATE CONDUCTED: 23 AUG 2010

D2783 - Four Ball EP-Oil: 0001675045	8/23/2010
Last Non-seizure Load (kg)	126.00
Load Wear Index ()	82.25
Weld Load (kg)	400.00

TEST SET 1B

BASELINE MEDIA: Shell SSGO w/t Duravi Gear Oil Additive

DATE CONDUCTED: 23 AUG 2010

D2783 - Four Ball EP-Oil: 0001675045	8/23/2010
Last Non-seizure Load (kg)	200.00
Load Wear Index ()	93.90
Weld Load (kg)	400.00

ADDITIONAL NOTES FROM LAB:

- Duravi Gear Oil Additive increased the Load Wear Index of the Base Media by approx. 15%
- Four Ball EP (Test Set 1B) – Ball and chuck at the last non-seizure load (200kg) was not nearly as hot as one would expect for that high of a load.